

TECHNICAL DATASHEET

Steni Nature FM

MATERIAL DATA (23 °C RF 45-60 %):		Value	Unit	Reference	
Thickness		5,5 ± 0,6	mm	STENI quality system	
Weight		12,0 ± 10 %	kg/m ²	STENI quality system	
Density		1960 ± 3 %	kg/m ³	STENI quality system	
Length and width		± 2	mm	STENI quality system	
Edge straightness		± 1	mm	STENI quality system	
Drilling position tolerance		± 5	mm	STENI quality system	
Diagonal deviation		≤ 3	mm	STENI quality system	
Angular deviation on L and U elements (100mm from corner)		± 3°	deg	STENI quality system	
SURFACE:					
Front side of panel: (Untreated natural aggregate)		Aggregate size	1,2 – 1,8	mm	STENI quality system
Front side quality: Uniform surface expression without craters and lack of aggregate)		<i>Product for outside use;</i> (5 m distance 90° viewing with normal daylight without sun) <i>Product for inside use;</i> (3 m distance 90° viewing with normal illumination)	Not visible		STENI quality system
Edge of panel:		<i>Untreated;</i> (small defects adjoining to surface)	Accepted		STENI quality system
Back side of panel is untreated. Minor defects.			Accepted		STENI quality system
PHYSICAL DATA:					
Flexural strength		≥ 30	N/mm ²	CSTB method	
Elasticity module		≥ 5000	N/mm ²	EN ISO 178	
Impact strength		≥ 17	kJ/m ²	ISO 172-82	
Tensile strength (length and width direction)		≥ 13	N/mm ²	ISO/R 527-66	
Critical radius		< 3,5	m		
Resistance to strong impact		Maximum height of ball drop	3,5	m	NT Build 066
Resistance of pull through panel (drilled hole d=5,5mm) Steni fixing screw (4,0 * 28/ 33)			1,0	kN	EN 320:1993
Emission After 28 days (23 °C 50 % RH)		TVOC Formaldehyde ∑ VOC carcinogenic	540 3 <1	µg/(m ² h)	EN ISO 16000-9:2006
Thermal conductivity λ _p			0,55	W/(m K)	SINTEF NBI
THERMAL PROPERTIES:					
Dimensional stability. Cumulative change max			0,04	%	NS EN 438-2:2005, part 18
Temperature expansion (-20 °C to +65 °C)			0,021- 0,026	mm/(m K)	SINTEF NBI
Water vapor resistance			30·10 ¹⁰	(m ² sPa)/kg	ASTM E 96-66
Water vapor resistance S _d			58,5	m	SINTEF NBI
Permeability of water vapour			33·10 ⁻¹³	kg/(m ² s Pa)	ASTM E 96-66
Water absorption 1 m deep: (25 °C 100% RH)		After 24 hours After 28 days	ca. 0,5 ca. 2,0	%	ASTM D-570
Frost resistance			> 300	Cycle	SINTEF NBI
FIRE RESISTANCE:					
Used as ventilated facade panel (surface)			B-s1,d0	Euro Class	EN 13501-1
ENVIRONMENTAL:					
Global warming potential			18	CO ₂ ekv/m ²	NEPD-2580-1307-EN
Total energy use			428	MJ/m ²	NEPD-2580-1307-EN